

Características técnicas Technical characteristics



| MODELO | Absorción de agua Water absorption | Resistencia a la flexión Breaking strenght | Resistencia a la helada Freezing resistance | PEI Resistencia a la abrasión Resistance to abrasion | MOHS Dureza Hardness | |
|---------|---------------------------------------|---|--|--|----------------------------|---|
| ARDISIA | Marfil | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Salmon | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Vison | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| CALIZA | Marfil | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Beige | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Noce | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Murano | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Marfil lapatto | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | CEMENT | Cement | <0,5 % | >35 N/mm2 | resiste / resists | 4 |
| | Anti-slip | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| CUIR | Marfil | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Nobuck | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Marron | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| IRON | Caldera | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Grafito | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Arena | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Gris | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| LANDER | Grafito | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Tabaco | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| LOFT | Pergamon | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Caramelo | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Café | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| NATURE | Marfil | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Ocre | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Rodeno | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Ocre lapatto | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| NORDICK | Haya | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Nogal | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| | Roble | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| ORION | Beige | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Terracota | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| PRISMA | Crema | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Perla | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Amaranto | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Gris | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Noce | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| PROYECT | Beige | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Nevada | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Moka | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| | Sombra | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Pirita | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| SHANGAI | Bianco | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Beige | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Ecrú | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Nero | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| SINTER | Sinter | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| SIQ | Siq | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| SLATE | Gris | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Negro | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| | Blanco | <0,5 % | >35 N/mm2 | resiste / resists | 5 | |
| STRATTA | Sand | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| | Grey | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |
| TULE | Blanco | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Negro | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| URBE | Arena | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Perla | <0,5 % | >35 N/mm2 | resiste / resists | 4 | |
| | Moka | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| | Carbon | <0,5 % | >35 N/mm2 | resiste / resists | 2 | |
| WOOD | Wood | <0,5 % | >35 N/mm2 | resiste / resists | 3 | |



| MODELO | | Resistencia choque térmico Thermal shock resistance | Resistencia al cuarteo Resistance to cracking | Manchas Stains | Agentes de limpieza Cleaning agents | Ácidos-bases Acids-bases |
|---------|----------------|--|--|-------------------|--|-----------------------------|
| ARDISIA | Marfil | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Salmon | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Vison | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| CALIZA | Marfil | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Beige | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Noce | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Murano | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| CEMENT | Marfil lapatto | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Cement | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| CUIR | Anti-slip | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Marfil | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| IRON | Nobuck | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Marron | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Caldera | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| LANDER | Grafito | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Tabaco | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Grafito | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| LOFT | Pergamon | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Caramelo | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Café | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| NATURE | Marfil | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Ocre | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Rodeno | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Ocre lapatto | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| NORDICK | Haya | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Nogal | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Roble | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| ORION | Beige | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Terracota | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| PRISMA | Crema | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Perla | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Amaranto | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Gris | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Noce | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| PROYECT | Beige | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Nevada | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Moka | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Sombra | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Pirita | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| SHANGAI | Bianco | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Beige | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Ecrú | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Nero | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| SINTER | Sinter | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| SIQ | Siq | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| SLATE | Gris | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Negro | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Bianco | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| STRATTA | Sand | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Grey | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| TULE | Blanco | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Negro | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| URBE | Arena | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Perla | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Moka | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| | Carbon | resiste / resists | resiste / resists | 5 | GA | GLA GHA |
| WOOD | Wood | resiste / resists | resiste / resists | 5 | GA | GLA GHA |